



**SURVIVABILITY • SUSTAINABILITY • MOBILITY
SCIENCE AND TECHNOLOGY
SOLDIER SYSTEM INTEGRATION**

TECHNICAL REPORT
NATICK/TR-95/006

AD _____

EVALUATION OF LASER-PROTECTIVE EYEWEAR DYES IN UVEX LENSES

by

**Leonard A. Levasseur, Joseph F. Roach, and
Kathryne B. Brubaker**

November 1994

Final Report

March 1992 - June 1992

Approved for Public Release, Distribution Unlimited

19950120 032

**UNITED STATES ARMY NATICK
RESEARCH, DEVELOPMENT AND ENGINEERING CENTER
NATICK, MASSACHUSETTS 01760-5000**

SCIENCE AND TECHNOLOGY DIRECTORATE



DISCLAIMERS

The findings contained in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of trade names in this report does not constitute an official endorsement or approval of the use of such items.

DESTRUCTION NOTICE

For Classified Documents:

Follow the procedures in DoD 5200.22-M, Industrial Security Manual, Section II-19 or DoD 5200.1-R, Information Security Program Regulation, Chapter IX.

For Unclassified/Limited Distribution Documents:

Destroy by any method that prevents disclosure of contents or reconstruction of the document.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE November 1994		3. REPORT TYPE AND DATES COVERED Final March 1992 - June 1992
4. TITLE AND SUBTITLE EVALUATION OF LASER-PROTECTIVE EYEWEAR DYES IN UVEX LENSES			5. FUNDING NUMBERS PE: 0602786A PR: AH98 TA: AOO WU: CAO	
6. AUTHOR(S) Leonard A. Levasseur, Joseph F. Roach Kathryne B. Brubaker				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Natick Research, Development and Engineering Ctr Kansas Street ATTN: SATNC-YSD Natick, MA 01760-5020			8. PERFORMING ORGANIZATION REPORT NUMBER NATICK/TR-95/006	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release, distribution unlimited			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Twenty-seven lenses of various dye combinations were received for testing from Uvex Corp. A previous contract from Uvex for Natick had failed the 240-hour Weatherometer test and this study was to determine which dye or which combination of dyes was responsible for this degradation. Dyes from different suppliers were incorporated into Uvex polycarbonate lenses. These dyes were laser blocking dyes obtained from Gentex, Polaroid, Barnes, Steadfast and Epolin (a Uvex dye) and used in various combinations within the lenses. These lenses were evaluated for optical density, visual transmittance, laser saturation, and solarization. Some of the lenses were tested in the weatherometer only.				
14. SUBJECT TERMS LASER PROTECTIVE GOGGLES LASER EYE PROTECTION EYE PROTECTION			15. NUMBER OF PAGES 20	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified		18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified		19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified
20. LIMITATION OF ABSTRACT				

TABLE OF CONTENTS

SECTION	Accession For	PAGE
	NTIS CRA&I <input checked="" type="checkbox"/>	
	DTIC TAB <input type="checkbox"/>	
	Unannounced <input type="checkbox"/>	
	Justification _____	
	By _____	
	Distribution /	
	Availability Codes	
	Dist Avail and/or Special	
	A-1	
LIST OF ILLUSTRATIONS		iv
PREFACE		v
SUMMARY		1
1.0 INTRODUCTION		1
2.0 TEST PROCEDURES		2
a. Properties Evaluated		2
b. Instrumentation/Method		2
3.0 RESULTS		7
a. Optical Density (Low Power Irradiation)		7
b. Optical Density (High Power Irradiation)		10
c. Visual Transmittance		11
d. Solarization		11
4.0 CONCLUSIONS		13
REFERENCES		14

LIST OF ILLUSTRATIONS

<i>FIGURES</i>	<i>PAGE</i>
1. Saturable Absorption Set-Up	5
2. Representative Spectra of Optical Density vs. Wavelength for Sample #070	9
3. Transmission Spectra Used for Measuring Photopic and Scotopic Transmittances	11
 <i>TABLES</i>	
1. Optical Density, Laser Saturation, Solarization Test Results	8
2. Optical Density of Sample #060	10

PREFACE

This study of 27 lenses of various dye combinations in Uvex Corporation lenses was undertaken during the period March 1992 to June 1992 by the authors at the US Army Natick Research, Development and Engineering Center. The funding was Program Element 0602786A, Project AH98, Task AOO and Work Unit CAO.

The citation of trade names in this report does not reflect an official endorsement of a product or item.

EVALUATION OF LASER PROTECTIVE EYEWEAR DYES IN UVEX LENSES

SUMMARY

Twenty-seven lenses for eye protection containing a combination of commercial dyes that were developed to absorb specific laser lines were tested for the following properties: optical density at the laser lines, laser saturation and resistance to weathering. The lenses were received from Uvex Corp and contained dyes from the following suppliers; Gentex Corp, Polaroid, EDO Barnes, Steadfast, Uvex and Epolin. Each dye was used in the Uvex spectacle configuration and was tested according to specifications MIL-STD-810E¹ Procedure II for solarization effects and optical density specifications as in MIL-G-0043914E(GL).²

1.0 INTRODUCTION

Dyes used as laser beam attenuators have been a major part of the laser eye protection program at Natick. The physical and environmental requirements imposed on dye performance criteria have proven difficult to achieve. Consequently, many types of dyes were developed that attempted to provide the required protection in a ballistic substrate that met all the specifications for laser eye protection for the individual soldier. This study of dye performance was initiated to determine the characteristics of each dye pertaining to test requirements and to compare the measured values with the specifications.

In addition this study was undertaken to characterize the synergistic properties of dye combinations in a polycarbonate substrate as used in the Uvex spectacle. The usual test criteria

were adhered to in the evaluation of the durability and protective properties of the laser-protective lens materials. The results of this study will provide guidance on the selection of the product to employ in the construction of protective eyewear to ensure proper protection for the wearer.

2.0 TEST PROCEDURES

a. PROPERTIES EVALUATED

In conformance with requirements, the following tests were performed by personnel from the U.S Army Natick Research Development and Engineering Center (NATICK), Science & Technology Directorate (S&TD), Fiber and Polymer Science Division (F&PSD), Technology Application Branch (TAB).

1. Spectrophotometric measurements of optical density and visual transmittance (photopic and scotopic).
2. Weatherometry: Resistance to solar radiation.
3. Laser Saturation: The measure of optical density change as a function of laser intensity.

b. INSTRUMENTATION/METHOD

The optical density of each sample is measured on a Perkin-Elmer Lambda 9 Spectrophotometer, Serial No. 1733. The Lambda 9 is a Double Monochromator, Double Beam Ratio Recording UV/VIS/NIR Spectrometer, which is capable of providing accurate photometric readings between 4 and 5 absorbance units directly. For lenses with relatively high absorbance values, a baseline correction is made using neutral density filters. Transmittance measurements (%T) are measured using the Perkin-Elmer Lambda 9 in the transmission mode, and the scotopic and photopic values are obtained using software developed at Natick.

The weatherometer studies are made using an Atlas Weatherometer Model Ci35 with controlled irradiance. The test setup and procedures are in conformance with those prescribed in MIL-STD-810E, Method 505.2, Procedure II.¹ The following test parameters and cycling times are used:

Irradiance level: 0.35 W/m²/nm, measured at 340 nm.

Weathering cycle: 20 hours of irradiation followed by 4 hours of darkness, repeated for 10 cycles.

Filtering: a borosilicate inner filter with a borosilicate (Type S) outer filter.

Temperature: 120° F (48° C) during the light portion of the cycle, and uncontrolled during the dark portion of the cycle.

Laser saturation measurements are made using the following instrumentation and criteria.

Laser: Custom built Q-switched Ruby/YAG laser manufactured by Continuum Corp, having an output of 75 mJ at 6943 nm (ruby) with a pulse width of 30 ns; 750 mJ at 1.06 micrometer with pulsewidths of 10, 20 and 30 ns; and 300 mJ at 532 nm with pulsewidths of 10, 20 and 30 ns.

Detector System:

Molelectron JD2000 Joulemeter Ratiometer Display

(S/N 1155)

Molelectron J_{3S-10} Joulemeter (S/N 162)

Molelectron J₃₋₀₉ Joulemeter (S/N 392)

Molelectron J-25 Joulemeter (S/N 962)

Newport FS-3 ND Filters (S/N 739)

Big Sky Software Corporation Multicam 2.1 Beam

Diagnostic System

Cohu Solid State Charge Couple Device (CCD) Camera,

Model 4800 (S/N 180811)

Figure 1 depicts the setup used in making saturable absorption measurements. By placing different combinations of neutral density (ND) attenuating filters at the laser output aperture, the user can vary the incident energy at the sample. ND filters also protect the reference detector and the CCD camera from damage. Another protective filter is placed at the throughput detector during baseline measurements or when a sample does not adequately attenuate the laser energy. A uniform energy distribution (top hat) is attained from a Gaussian distribution by a pair of lenses and an aperture. The beam is expanded with a plano-concave lens ($f=-51.4$ mm) and then recollimated by a plano-convex lens ($f=97.5$ mm) placed at a distance, d , equal to the sum of the two focal lengths ($d=46.1$ mm). A fixed diameter (5 mm) aperture placed prior to the sample limits the impinging radiation to that of a top hat energy distribution with a known area (0.196 cm²).

After the optical components are aligned, the beam profile is optimized by placing a CCD camera at the laser output. While monitoring the output beam, the laser cavity is adjusted to produce a near Gaussian distribution. The camera is then moved to the throughput detector's position to verify a top hat distribution at the sample. The throughput detector is subsequently returned to its position in the optical path. Pulse width is determined by a photodetector and oscilloscope.




Figure 1. Saturable Absorption Setup

The requirement contained in MIL-STD-810E¹ mandates that each sample will be tested at 1MW/cm² without degrading the optical density to a value below that required by the specification. The test procedure is as follows. The incident energy is calculated according to (eqn. 1):

$$E = I \cdot t_p \cdot A \quad (1)$$

where,

E = incident energy (J)

I = irradiance on the sample (MW/cm²)

t_p = pulse duration (seconds)

A = area (cm²)

The required incident energy density (approximately 2 mJ over an area of 0.196 cm²) is attained by trial and error combinations of ND filters at the laser output aperture. The pulse width used is 10ns to give approximately 1MW/cm². A baseline measurement is

established by averaging the energy at the reference and the throughput detectors for 25 shots. Due to damage threshold limits on the detector, a ND filter is sometimes required in front of the throughput detector during baseline measurements. The protective ND filter is replaced with a sample of unknown optical density (OD) and the energy at the two detectors is again recorded and averaged for 25 shots.

Optical density is defined by (eqn. 2):

$$OD = \log_{10}(1/T) \quad (2)$$

where T is the measured transmission (output/input).

A normalization constant, k, is calculated by (eqn. 3):

$$k = E_r/E_{r'} \quad (3)$$

where E_r = average reference energy during baseline measurement (J)

$E_{r'}$ = average reference energy during sample measurement (J)

The OD of the sample is then calculated by (eqn. 4):

$$OD = A + \log(k*(E_t/E_{t'})) \quad (4)$$

where k = normalization constant defined above

A = OD of ND filter at sample detector during baseline measurement

E_t = average throughput energy during baseline measurement (J)

$E_{t'}$ = average throughput energy during sample measurement (J)

A value of the optical density lower than that obtained with the spectrophotometer would indicate the occurrence of saturable absorption.

3.0 RESULTS

Table 1 shows the results obtained in testing for optical characteristics. These include optical densities, tested under low power using the Perkin Elmer Lambda 9 Spectrophotometer and under high power using laser radiation, scotopic and photopic transmittances and weatherometer tests. Multiple manufacturers as noted in the table represent dyes for L1, L2 and L3 in that order.

a. OPTICAL DENSITY (LOW POWER IRRADIATION)

Table 1 shows the optical densities measured with the Lambda 9 spectrophotometer. A representative spectrum is shown in Figure 2. Curve A is the spectrum before weatherometer testing and B after.

The majority of the samples met the initial optical density requirement of 4.0 or greater. However, samples #006, 035, 062, 063, 068 and 069 fell below this level at one or more of the required wavelengths. In the measurement of optical density a difference was noted from that reported by Uvex. Further investigation showed that by repositioning the lens, an optical density of equal or greater than that reported from Uvex was found. For instance, measurement of sample #060 showed a difference of 0.74 OD units at 1064 nm over the front surface. Several of the other samples also exhibited similar differences.

Table 1. Optical Density, Laser Saturation, Solarization Test Results (nm)

SMP	LAMBDA 9			LASER SATURATION			WEATHEROMETER			TRANSM %		MFG*
	532	694	1064	532	694	1064	532	694	1064	PHOT	SCOT	
002	4.6	---	---	4.3	---	---	---	---	---	36	17	B
003	4.0	---	---	>4	---	---	---	---	---	48	8	B
005	4.0	---	---	---	---	---	4.1	---	---	---	---	U
043	4.3	---	---	---	---	---	4.4	---	---	29	16	S
010	---	5.7	---	---	3.1	---	---	5.8	---	64	77	S
025	---	---	3.9	---	---	3.8	---	---	3.5	36	28	E
032	---	---	4.9	---	---	---	---	---	3.6	---	---	P
054	---	---	5.6	---	---	>5	---	---	4.8	43	30	E
055	---	---	5.4	---	---	>5	---	---	4.8	17	11	E
058	---	---	4.4	---	---	4.5	---	---	3.9	18	12	E
059	---	---	5.4	---	---	>5	---	---	4.7	46	33	E
060	---	---	4.3	---	---	4.6	---	---	4.1	27	17	E
063	---	---	3.2	---	---	3.3	---	---	---	22	21	S
026	4.2	5.4	---	---	---	---	4.0	5.4	---	13	12	S
006	4.4	---	3.4	---	---	---	4.3	---	3.1	22	3	P
076	4.1	---	4.4	---	---	---	1.9	---	2.3	---	---	G
027	---	6.0	5.5	---	>4	>5	---	5.9	4.8	16	12	S/E
031	---	5.8	5.1	---	---	---	---	5.1	4.1	---	---	P
071	---	5.1	5.1	---	3.6	3.9	---	5.1	5.2	25	27	P
030	4.7	5.9	5.0	---	---	---	4.6	5.3	4.5	---	---	P
035	4.6	6.0	2.8	---	---	---	4.6	6.1	2.7	---	---	UGG
044	4.5	3.8	4.9	---	---	---	4.5	3.8	4.9	---	---	USE
062	3.3	5.4	5.2	---	---	---	2.9	5.0	5.2	---	---	BBE
068	4.8	5.2	2.9	>4	4.0	3.1	4.9	5.3	3.2	3	1	SSE
069	4.1	5.5	1.5	4.1	>4	1.6	3.8	5.8	1.8	6	3	SGG
070	4.0	6.1	4.0	3.9	>4	3.2	3.3	5.0	3.2	8	6	SSP
072	4.1	5.1	4.6	4.4	4.3	3.6	4.2	5.0	4.2	12	3	P

*B=EDO BARNES; U=UVEX; G=GENTEX; P=POLAROID; E=EPOLIN; S=STEADFAST




Figure 2. Representative Spectra of Optical Density vs Wavelength for Sample # 070. Curve A is Before Weatherometer Test and B After.

The optical density of sample #060 in particular, was measured at four locations along the right lens and left lens with the following results (Table 2):

Table 2. Optical Density of Sample 060			
position	left lens	position	right lens
1	4.90	1	4.29
2	4.95	2	4.37
3	5.03	3	4.61
4	4.94	4	4.65

The variation in optical density (absorbance) for this sample ranged from 4.29 to 5.03. These results indicate that the dye was not distributed evenly in the polycarbonate.

b. OPTICAL DENSITY (HIGH POWER IRRADIATION)

Sixteen of the lenses were tested for laser saturation. Sample 010 showed a loss of greater than 2.5 optical units when tested at 694 nm. Samples 071 and 072 were affected at both 694 and 1064 nm, and 068 at 694. In no instance was the optical density at 532 nm affected.

c. VISUAL TRANSMITTANCE

Values for photopic and scotopic (PHOT, SCOT) transmittances are shown in Table 1. Transmission curves for two samples (Figure 3) are typical examples of data used in calculating transmittance values.

The photopic transmittance relates to day vision and the scotopic to night vision. The critical parameter for visual transmittance is the scotopic value since reduction of light during the day is sometimes desired. As a general rule, transmittances of 40% or better are accepted as useful for both day and night use. As can be seen from the data in Table 1, current dye technology precludes its use for eye protection for both day and night operation due to the very low transmittances in three line configurations. In fact, the only sample in table I that meets the 40% criteria is for single laser line attenuation (sample 010) but this sample did not meet the optical density requirement when tested for saturation.

d. SOLARIZATION

Twenty four of the lenses were exposed in the weatherometer for 240 hours (10 days). Of the 13 lenses tested at 532 nm, samples 076 and 070 were significantly affected by solarization (loss of 0.5 optical density units or greater). At 1064 nm, 10 of the lenses lost 0.5 to 2 in optical density units. In some cases this would not have excluded the use of these dyes since the optical density remained over 4.0 and would have met the requirement. However, it does point out the susceptibility of the 1064 dye to fading and hence should be monitored for compliance with the specifications. At 694 nm three samples, 031, 030 and 070, were significantly affected. However all three remained over the required optical density of 4.0.





Figure 3. Transmission Spectra Used for Measuring Photopic and Scotopic Transmittances.

4.0 CONCLUSIONS

The object of this report is to initiate a data base study on the performance of various dyes as laser line attenuators. In addressing the optical densities necessary for laser eye protection in a ballistic substrate, the lenses performed as expected. The data accumulated point out the deficiencies of certain dyes alone as well as of some dye combinations in laser saturation testing and solarization. It is difficult to assess all the ramifications inherent in combining different dyes because of the differences noted in the performance of materials from the same manufacturer. For example, sample 032 from Polaroid showed a significant decrease in the optical density of the 1064 nm dye after testing in the weatherometer. Yet the same test on sample 006, another Polaroid sample but with attenuation for two wavelengths 532nm and 1064 nm, did not show significant changes. It would have been easier to assume a synergistic effect from the combination of the 532 nm and 1064 nm dyes if the initial optical densities at 1064nm had been the same. In any case, there is evidence that synergism in dye combinations affects the performance of the individual dyes.

REFERENCES

1. Department of Defense, MIL-STD-810E, Solar Radiation, 14 July 1989.
2. Department of Defense, MIL-G-0043914E(GL), Goggles, Sun, Wind and Dust, 26 Nov 1990.

This document reports research undertaken at the U.S. Army Natick Research, Development and Engineering Center and has been assigned No. NATICK/TR-~~95~~⁹⁵/006 in the series of reports approved for publication.